

## Claims

1. A gel for application to a wound, comprising a mixture of citrus complex carbohydrates, a cellulose derivative, a polyol component and water, wherein said citrus complex carbohydrates are cross-linked to said cellulose derivative by an ionic cross-linking agent.
2. A gel according to claim 1, wherein said cellulose derivative is a carboxymethyl cellulose derivative.
3. A gel according to claims 1 or 2, wherein said cellulose derivative is sodium carboxymethyl cellulose.
4. A gel according to any one of the preceding claims, wherein said polyol component is a dihydroxyalkane having from 2 to 6 carbon atoms.
5. A gel according to claim 4, wherein said dihydroxyalkane is 1,2-dihydroxypropane.
6. A gel according to any one of claims 1 to 3, wherein said polyol component is a polyhydroxyalkane of the general formula
$$C_nH_{(2n+2)}O_n$$
wherein n is an integer of from 3 and 6.
7. A gel according to claim 6, wherein said polyol component is polyethylene glycol.
8. A gel according to claim 7, wherein said polyethylene glycol has a molecular weight in the range of from 200 to 600.
9. A gel according to any one of the preceding claims,

wherein said ionic cross-linking agent is a multivalent ion

10. A gel according to any one of the preceding claims,  
5 wherein said ionic cross-linking agent is a divalent ion.

11. A gel according to claim 10, wherein said divalent  
10 ion is a magnesium ion.

12. A gel according to claim 10, wherein said divalent  
ion is a calcium ion.

13. A gel according to any one of the preceding claims,  
15 wherein said citrus complex carbohydrates have been  
extracted from citrus fruit peel by leaching using an  
aqueous medium.

14. A gel according to claim 13, wherein said aqueous  
20 medium is hot acidified water.

15. A gel according to any one of claims 1 to 14,  
wherein said citrus complex carbohydrate is a low ester  
carbohydrate.  
25

16. A gel according to any one of the preceding claims,  
wherein said citrus complex carbohydrate comprises from  
0.01 to 10% by weight of the gel.

30 17. A gel according to claim 16, wherein said citrus  
complex carbohydrate comprises about 2.8% by weight of  
the gel.

18. A gel according to any proceeding claim, wherein  
35 said cellulose derivative comprises from 0.01% to 10%

by weight of the gel.

19. A gel according to claim 18, wherein said cellulose derivative comprises about 3.7% by weight of the gel.

5

20. A gel according to any preceding claim, wherein said polyol component comprises from 0.1 to 30% by weight of the gel.

10 21. A gel according to any preceding claim, wherein said polyol comprises about 14.4% by weight of the gel.

15 22. A gel according to any preceding claim, wherein said ionic cross-linking agent comprises from 0.01 to 5% by weight of the gel.

20 23. A gel according to any preceding claim, wherein said ionic cross-linking agent comprises about 0.9% by weight of the gel.

20

24. A gel according to any preceding claim, wherein said gel has been sterilised.

25 25. A gel according to any preceding claim, wherein said gel further comprises at least one of the following components: an anti-bacterial agent; an anti-fungal agent; an anti-mycotic agent; an anaesthetic; an additional debriding agent; an anti-inflammatory agent; a growth factor; an enzyme; a pharmaceutical composition; vitamins; amino acids; aloe vera or trace metals.

30

35 26. A gel according to any preceding claim, wherein said gel comprises 2.8% by weight citrus complex carbohydrate, 3.7% by weight cellulose derivative,

14.4% by weight polyol, 0.9 % by weight ionic cross-linking agent and 78.2% by weight water.

27. A process for making a gel, comprising the steps of:  
5       mixing a citrus complex carbohydrate, a cellulose derivative and an ionic cross-linking agent in aqueous solution to effect formation of ionic bonds between said citrus complex carbohydrate and said cellulose derivatives; and  
10       adding a polyol to the mixture to form a gel.

28. A process according to claim 27, comprising the steps of:  
      preparing a first aqueous solution comprising a  
15       citrus complex carbohydrate;  
      Preparing a second aqueous solution comprising a cellulose derivative;  
      preparing a third aqueous solution comprising an ionic cross-linking agent;  
20       blending said first, second and third solutions to effect formation of ionic bonds between said citrus complex carbohydrate and said cellulose derivatives; and adding a polyol to the blended solutions to form a gel.

25       29. A process according to claim 27 or 28, substantially as described in the Example.

30       30. A process according to any one of claims 27 to 29 substantially as hereinbefore described.

31. A wound dressing comprising a gel in accordance with any one of claims 1 to 26.

35       32. A bacteriostatic gel comprising a mixture (repeat

feature of claim 1).